

Technical Data Sheet



Company Overview

Vivasil Paints (M) Sdn Bhd is a manufacturing and supplying paint coating products.

Our company has witnessed accelerated growth and development under the prudent management.

Our company produces the full range of architectural paints construction materials and industrial paints for local market and oversea markets.

Vivasil color products has widened to include specialist and designer products.

For more information:

Email: enquiry@vivasil.com

Facebook:
www.facebook.com/vivasilpaints

Website: www.vivasil.com

Youtube:
<https://youtu.be/E3UaautZ5X4>

Vivasil 225 Solventless Epoxy



Vivasil 225 Solventless Epoxy is a two component product supplied in 18 litre kits part A & B which contain the proper ratio of ingredients. The entire contents of each container must be mixed together. After mixing the base portion, add the epoxy hardener part B slowly with part A continued agitation. After the hardener Part B add is complete, continue to mix slowly until homogeneous. The pot life of the mixed material is 30 minutes at 25 C. Higher temperatures will reduce the working life of the coating - lower temperatures will increase it. Stir before use. Place in cool & dry. Close tight after use. Available in 1, 5 and 18 litres two pack system standard colour cards.

PREPARATION OF SURFACE

All the surface must be dry, clean and free from contaminants such as dust, dirt, moss/fungus, oil, grease and ridges etc. recommended use acid wash and let it dry overnight before sealer application.

Vivasil 225 solventless Epoxy coating is a durable, heavy duty, two-part epoxy coating designed to provide abrasion and chemical resistance. Vivasil 225 solventless Epoxy cures to a smooth glossy finish which is easily cleaned and resistance to a wide variety of chemical spillage and fumes makes it ideal for use in a wide range of industrial environments such as car parks, production areas, hospitals, petrol stations, schools, churches, vehicle workshops and warehouses. 225 solventless 225 Epoxy will take between 24 hours to cure enough to walk on

Recommended
Theoriat coverage : 5 to 8 m2 per litre
Base Epoxy Resin Solution
Consistency Liquid
Curing System Polyamide cured
Colour special or standard color card system
Potlife @ 65% R.H 30 minutes
Drying Time 10C – 240 min
20C – 90 min
30C – 60 min
Full cure 3 days at 23oC
Overcoat Time 10C – 120 min
20C – 60 min
30C – 45 min
24 hours for all other coatings

* If you have any paint related questions please call our customer careline at **06-790 9222**

VIVASIL PAINTS (M) SDN. BHD. (1117204-T)

167, Jalan Nilai 3/16, Kawasan Perindustrian Nilai 3,
71800, Nilai, Negeri Sembilan,

Tel ; 606-790 9222 Malaysia

Email address : enquiry@vivasil.com Website : www.vivasil.com

Facebook: www.facebook.com/vivasilpaints

