

Technical Data Sheet



Company Overview

Vivasil Paints (M) Sdn Bhd is a manufacturing and supplying paint coating products.

Our company has witnessed accelerated growth and development under the prudent management.

Our company produces the full range of architectural paints construction materials and industrial paints for local market and oversea markets.

Vivasil color products has widened to include specialist and designer products.

For more information:

Email: enquiry@vivasil.com

Facebook:
www.facebook.com/vivasilpaints

Website: www.vivasil.com

Youtube:
<https://youtu.be/E3UaautZ5X4>

Vivasil 563 Acrylic Floor Coat



Vivasil 563 Acrylic Floor Coat is a thermoplastic solvent base Acrylic multi propose floor coat are one component floor coating for flooring ,concrete,pavers, and bituminous road surface. Vivasil 563 Acrylic Floor Coat is an interior or exterior, high gloss, industrial grade solvent borne floor coating.Vivasil 563 Acrylic Floor Coat is fast curing for shorter times and will not affect taste of food during installation and cure time.

PREPARATION OF SURFACE

All the surface must be dry, clean and free from contaminants such as dust, dirt, moss/fungus, oil, grease and ridges etc.Cracks, Chips Voids and Damages should be repaired.good flow out of application marks (e.g. brush-marking) forming a continuous protective film. quick drying

Storage:

Store in closed containers at temperature below 32oC and away from heat sources and sunlight. When properly stored, will remain stable for 12 months from date of delivery.

Resin type.....	Oil-modified Acrylic
Solids content.....	35% (by volume)
Typical film thickness (per coat).....	25 microns (dry)75 microns (wet)
Theoretical coverage.....	10-12m ² / L @ 25 microns dry film thickness
Touch dry.....	10 - 15 minutes
Hard dry.....	24 hours
Recoating.....	
Gloss.....	Semi Gloss
Colours.....	standard color card or tinting system
Shelf life.....	minimum 12 months (in cool, dry conditions)
Airless Spray nozzle size.....	0.33 – 0.38 mm
nozzle pressure.....	2000 – 2500 psi (14 - 17mPa)
volume of thinner.....	up to 10%
Air Spray nozzle size.....	1.6 – 2.0 mm
nozzle pressure.....	45 – 60 psi (300 - 400kPa)
volume of thinner.....	up to 30%
Cleaning solvent	Vivasil Thinner

* If you have any paint related questions please call our customer careline at **06-790 9222**

VIVASIL PAINTS (M) SDN. BHD. (1117204-T)

167,Jalan Nilai 3/16, Kawasan Perindustrian Nilai 3,
71800, Nilai ,Negeri Sembilan,
Tel ; 606-790 9222 Malaysia

Email address : enquiry@vivasil.com Website : www.vivasil.com

Facebook: www.facebook.com/vivasilpaints

