Technical Data Sheet

VIVASIL™
PROVEN PAINT TECHNOLOGY

GERMAN TECHNOLOGY

Company Overview

Vivasil Paints (M) Sdn Bhd is a manufacturing and supplying paint coating products.

Our company has witnessed accelerated growth and development under the prudent management.

Our company produces the full range of architectural paints construction materials and industrial paints for local market and oversea markets.

Vivasil color products has widened to include specialist and designer products.

For more information:

Email: enquiry@vivasil.com

Facebook: www.facebook.com/vivasilpaints

Website: www.vivasil.com

Youtube: https://youtu.be/E3UaautZ5X4

Vivasil 873 Epoxy Damp Blocker





Vivasil 873 Epoxy Damp Blocker is a two component product supplied in 1,5 and 20 litre kits part A & B which contain the proper ratio of ingredients. The entire contents of each container must be mixed together. After mixing the base portion, add the epoxy hardener part B slowly with part A continued agitation. After the hardener Part B add is complete, continue to mix slowly until homogeneous.The pot life of the mixed material is 30 minutes at 25 C. Higher temperatures will reduce the working life of the coating - lower temperatures will increase it.. Stir before use. Place in cool & dry. Close tight after use. Available in 1, 5 and 18 litres two pack system standard colour cards.

PREPARATION OF SURFACE

All the surface must be dry, clean and free from contaminants such as dust, dirt, moss/fungus, oil, grease and ridges etc.recommended use acid wash and let it dry overnight before sealer application.

Vivasil 873 Epoxy Damp Blocker is a two component product part A & B.This two-part Epoxy Damp Blocker is a low-odor, low-volatility solution that dramatically reduce Moisture and dampening levels, improving the integrity and durability of any concrete floor.Vivasil 873 Epoxy Damp Blocker works by penetrating into concrete to create an Moisture blocking barrier.Epoxy damp blockers are aways to protect concrete floors from rising damps

Recommended
Theorial coverage : 5 to 8 m2 per litre
Base Epoxy Resin Solution
Consistency Liquid
Curing System Polyamide cured
Colour Clear
Potlife @ 65% R.H 30 minutes
Drying Time 10C – 240 min
20C – 90 min
30C – 60 min
Full cure 3 days at 23oC
Overcoat Time 10C – 120 min
20C – 60 min
30C – 45 min
24 hours for all other coatings

* If you have any paint related questions please call our customer careline at ***06-790 9222***

VIVASIL PAINTS (M) SDN. BHD. (1117204-T)
167,Jalan Nilai 3/16, Kawasan Perindustrian Nilai 3,
71800, Nilai ,Negeri Sembilan,
Tel ; 606-790 9222 Malaysia
Email address : enquiry@vivasil.com Website : www.vivasil.com
Facebook: www.facebook.com/vivasilpaints