Technical Data Sheet

VIVASIL™ PROVEN PAINT TECHNOLOGY

GERMAN TECHNOLOGY

Company Overview

Vivasil Paints (M) Sdn Bhd is a manufacturing and supplying paint coating products.

Our company has witnessed accelerated growth and development under the prudent management.

Our company produces the full range of architectural paints construction materials and industrial paints for local market and oversea markets.

Vivasil color products has widened to include specialist and designer products.

For more information:

Email: enquiry@vivasil.com

Facebook: www.facebook.com/vivasilpaints

Website: www.vivasil.com

Youtube: https://youtu.be/E3UaautZ5X4

Vivasil 632 Epoxy Tile Sealer





Vivasil Epoxy 632 Tile Sealer Paint (Solvent Base) is a two component solvent based tile wall or floor Sealer Part A resin and Part B Hardener. Vivasil Epoxy 632 Tile Sealer Paint offers good chemical and abrasion resistance as a base coat layer for solvent base epoxy coatings and solvent base polyurethane coating . Vivasil Epoxy 632 Tile Sealer Paint is specially formulated for use as a surface primer for seamless flooring applications to provide superior adhesion of epoxy and urethane top coats. Recommended as a primer base coat for Vivasil 631 Epoxy Tile Paint.Stir before use. Place in cool & dry. Close tight after use. Available in 1 and 5 litres.

MIXING

Vivasil 632 Part A and B are shaken before pouring and mixing. The mixing ratio for is 4 Parts Resin (Part A) to 1 Part Hardener (Part B) by volume; graduated plastic mixing containers are recommended for measuring volumetric quantities. Part B is to be added to Part A and mixed at low speed with a spatula.Mix only enough material for immediate use. Care should be taken to minimize air introduced during mixing. Mix until a smooth and homogeneous mixture is formed, free of striations. This should take approximately 1 minute. Ensure material from the bottom and edges of the pail are sufficiently mixed. Let material stand for 1 minute. Mix for an additional minute.

Recommended
Theorial coverage :3 to 5 m2 per litre
Base Epoxy Resin Solution and hardener
Consistency Liquid
Curing System Polyamide cured
Colour : White
Potlife @ 65% R.H 30 minutes
Drying Time 10C – 240 min
36C – 24 hour
Full cure 3 days at 23oC
Overcoat Time 40C – 120 min
24 hours for all other coatings

* If you have any paint related questions please call our customer careline at ***06-790 9222***

VIVASIL PAINTS (M) SDN. BHD. (1117204-T)
167,Jalan Nilai 3/16, Kawasan Perindustrian Nilai 3,
71800, Nilai ,Negeri Sembilan,
Tel ; 606-790 9222 Malaysia
Email address : enquiry@vivasil.com Website : www.vivasil.com
Facebook: www.facebook.com/vivasilpaints