

Technical Data Sheet



Company Overview

Vivasil Paints (M) Sdn Bhd is a manufacturing and supplying paint coating products.

Our company has witnessed accelerated growth and development under the prudent management.

Our company produces the full range of architectural paints construction materials and industrial paints for local market and oversea markets.

Vivasil color products has widened to include specialist and designer products.

For more information:

Email: enquiry@vivasil.com

Facebook:
www.facebook.com/vivasilpaints

Website: www.vivasil.com

Youtube:
<https://youtu.be/E3UaautZ5X4>

Vivasil 920 Non Slip Epoxy Coating



Vivasil 920 Non Slip Epoxy Coating is a two-component epoxy solvent-based coating. As a result, this anti-slip product adheres perfectly to all types of shower and toilet surfaces, tile floors and all types of concrete floor surfaces. The existing surfaces coating can be removed or without removing and wont affected the surface. Vivasil 920 Epoxy Paint will take between 12 and 24 hours to cure enough to walk on, but the curing process is not complete until the epoxy has fully hardened. This can generally take up to 72 hours, depending on the temperate and humidity of the surroundings entire contents of each container must be mixed together. The pot life of the mixed material is 30 minutes at 25 C. Surface must properly primed with Vivasil Solventless Epoxy Sealer before application. Stir before use. Place in cool & dry. Close tight after use. Available in 1 and 5 litres two pack system standard colour cards.

Storage:

Store in closed containers at temperature below 32oC and away from heat sources and sunlight. When properly stored, will remain stable for 12 months from date of delivery.

Resin type.....	Epoxy resin , Fillers, aggregate and Hardener
Solids content.....	65% (by volume)
Typical film thickness (per coat).....	75 microns (dry) 75 microns (wet)
Theoretical coverage.....	5-6m ² / L @ 25 microns dry film thickness
Touch dry.....	24 hours
Hard dry.....	72 hours to 7 days
Recoating.....	24 hours
Gloss.....	Gloss finish
Colours.....	Standard colour brochure or special mix colour
Shelf life.....	Minimum 12 months (in cool, dry conditions)
Mixed pot life.....	25 minute to 35 minute
Dilution.....	166 epoxy thinner
Volume of thinner.....	10 to 15%
Curing time.....	20 to 30 minute
Curing temperature.....	36 Celcius
Sand paper.....	N.A
Tools.....	Brush , roller or spray
Cleaning solvent	Thinner
Vehicles	Resin, curing agent, aggregates and fillers

* If you have any paint related questions please call our customer careline at **06-790 9222**

VIVASIL PAINTS (M) SDN. BHD. (1117204-T)

167, Jalan Nilai 3/16, Kawasan Perindustrian Nilai 3,
71800, Nilai ,Negeri Sembilan,

Tel ; 606-790 9222 Malaysia

Email address : enquiry@vivasil.com Website : www.vivasil.com

Facebook: www.facebook.com/vivasilpaints

