Technical Data Sheet

VIVASIL™ PROVEN PAINT TECHNOLOGY

GERMAN TECHNOLOGY

Company Overview

Vivasil Paints (M) Sdn Bhd is a manufacturing and supplying paint coating products.

Our company has witnessed accelerated growth and development under the prudent management.

Our company produces the full range of architectural paints construction materials and industrial paints for local market and oversea markets.

Vivasil color products has widened to include specialist and designer products.

For more information:

Email: enquiry@vivasil.com

Facebook: www.facebook.com/vivasilpaints

Website: www.vivasil.com

Youtube: https://youtu.be/E3UaautZ5X4

Vivasil 839 Solvent Free Epoxy Clear





Vivasil 839 Solvent Free Epoxy Clear is a high quality high build two component solvent free epoxy clear coating for application to new and existing timber floors and woods substrates. It provides a smooth, easily cleaned surface which is resistant to dirt, moisture, oil, light-medium abrasion and chemical attack. It is formulation enhanced by the use of a fast acting hardener that can cure at lower temperatures compared to standard amine hardeners. Vivasil 839 its not contain any solvents, more durable and eco friendly product.The curing process will take between 12 and 24 hours to cure enough to walk on.Vivasil 839 is a medium viscosity epoxy system that cures to a clear and tough finish clear coat can be use as finishing clear coat .It can be used on any wood or cabinetry interior surfaces. Clear coat acts as a protection layer that protects the epoxy top coat color from losing his adhesion and discolouration.Pot life of the mixed material is 30 minutes at 25 C.Available in 1 and 5 litres.

Storage:
Store in closed containers at temperature below 32oC and away from heat sources and sunlight. When properly stored, will remain stable for 12 months from date of delivery.

Resin type.....Epoxy resin and Hardener
Solids content..... 85% (by volume)
Typical film thickness (per coat).....25 microns (dry)75 microns (wet)
Theoretical coverage..... 10-12m2 / L @ 25 microns dry film thickness
Touch dry.....24 hours
Hard dry..... 72 hours to 7 days
Recoating..... 24 hours
Gloss.....Gloss finish
Colours.....Clear
Shelf life..... Minimum 12 months (in cool, dry conditions)
Mixed pot life.....N.A
Dilution.....N.A
Volume of thinner..... No Dilution
Curing temperature.....N.A
Sand paper.....
Tools.....Brush ,roller or spray
Cleaning solvent ..... Thinner
Vehicles ..... Resin,curing agent and fillers

* If you have any paint related questions please call our customer careline at ***06-790 9222***

VIVASIL PAINTS (M) SDN. BHD. (1117204-T)
167,Jalan Nilai 3/16, Kawasan Perindustrian Nilai 3,
71800, Nilai ,Negeri Sembilan,
Tel ; 606-790 9222 Malaysia
Email address : enquiry@vivasil.com Website : www.vivasil.com
Facebook: www.facebook.com/vivasilpaints