

Technical Data Sheet



Company Overview

Vivasil Paints (M) Sdn Bhd is a manufacturing and supplying paint coating products.

Our company has witnessed accelerated growth and development under the prudent management.

Our company produces the full range of architectural paints construction materials and industrial paints for local market and oversea markets.

Vivasil color products has widened to include specialist and designer products.

For more information:

Email: enquiry@vivasil.com

Facebook:
www.facebook.com/vivasilpaints

Website: www.vivasil.com

Youtube:
<https://youtu.be/E3UaautZ5X4>

Vivasil 3003 SFC Lime Super Fine Coat



Vivasil 3003 SFC Lime Plaster Super Fine Coat is a finishing smooth layer must be apply after the middle base coat or float layer Scrape off any stray high-spots or gritty bits from the previous coat. Heavily dampen the underlying plaster with clean water using a brush or mister. It should be damp to the touch but with no standing water left on the surface. Lime plasters require moisture in the background to prevent the super fine layer from drying out too fast and peeling. Mixing the 3003 Super Fine Paste dry powder with clean water using a high speed mechanical paddle mixer for 5 minutes, the super fine coat should be creamy, smooth, and lump-free resembling natural yogurt or thick cream. Load the creamy paste onto a clean stainless steel finishing trowel. Apply a second ultra-thin layer immediately (wet-on-wet) while the first pass is still tacky and receptive. This consolidates the two passes into a dense, solid, ultra-fine skin. Let the plaster "steady up" and lose its wet sheen. Run a damp fine-grain orange sponge float over the surface in light, circular motions. For a silky-smooth, premium finish, follow up right behind the sponge by skimming a clean, dry stainless steel finishing trowel flat against the surface to compress and close the lime plaster.

Protect outdoor walls from scorching direct sun and driving wind using protective tarpaulins.

Quick Application Steps

Prepare: Clean your target wall of dust and debris. Pre-dampen porous masonry to control water absorption.

Mix: Gradually combine the Vivasil 25 kg dry mix with 9 litres of clean water until it reaches a thick, uniform, heavy batter consistency.

Trowel: Apply a firm initial scratch coat to establish a bond, then build out the main layer up to 8mm–10mm.

Key & Cure: Drag a plastering comb across the surface while wet to create a key. Lightly mist with water over the next few days to allow slow, optimal curing.

Mixing the Plaster

Stir the powder without clots into the required amount of clean, cold water using a powerful electric drill with a paint stirrer. After an expanding time of approx. 5 minutes, stir again thoroughly.

Storage:

Store in closed containers at temperature below 32°C and away from heat sources and sunlight. When properly stored, will remain stable for 12 months from date of delivery.

Vivasil 3000 SC -Lime Plaster Scratch Coat

Vivasil 3001 BC Lime Plaster Base Coat

Vivasil 3002 MC Lime Plaster Middle Coat

Vivasil 3003 SFC Lime Plaster Super Fine Coat

One coat of Vivasil 801 Silicone sealer

Two coat of Vivasil Weatherseals Silicone Paint

* If you have any paint related questions please call our customer careline at **06-790 9222**

VIVASIL PAINTS (M) SDN. BHD. (1117204-T)

167, Jalan Nilai 3/16, Kawasan Perindustrian Nilai 3,

71800, Nilai, Negeri Sembilan,

Tel ; 606-790 9222 Malaysia

Email address : enquiry@vivasil.com Website : www.vivasil.com

Facebook: www.facebook.com/vivasilpaints

